
Zitrec IC

1 Description

Zitrec IC is a water-based superconcentrate of organic inhibitors, which requires dilution at concentration levels between 3 and 6% before final use. This low dosage, in combination with the all-round protection **Zitrec IC** delivers, makes it an excellent economical solution.

Zitrec IC is used in heating and cooling systems in both domestic and industrial applications using water or a glycol/water mixture.

Zitrec IC is also suitable to inhibit fluids used in heat pumps, floor heating systems and air-conditioning units.

2 Benefits

Most water systems suffer from many different types of corrosion. **Zitrec IC** dilutions or **Zitrec IC added** to water/glycol systems offer the following benefits to the user:

- **all round corrosion protection** through synergistic combination of additives
- **non-scaling additives** thanks to the absence of mineral inhibitors
- **no yearly additions required**
- **non-hazardous product**
- **compatible with common seal materials**
- **stable in hard water** thanks to the absence of silicates & phosphates
- **exempt from borates and not classified** under the criteria of Directive 1999/45/EC

Contrary to today's solutions, this corrosion inhibitor does not create a thick scale but creates a very thin layer of inhibitors, just one molecule thick. Thanks to the nature of the inhibitors selected, the metal surfaces are effectively protected for their full life time.

3 Use concentrations of Zitrec IC

A normal use concentration of 6% v/v is recommended. In heating systems where predominantly carbon steel, copper and cast iron is used, a use ratio of minimal 3% v/v is recommended.

A system filled with **Zitrec M** (ethylene glycol based) or **Zitrec L** (propylene glycol based) may be boosted using **Zitrec IC**. To calculate the exact requirement of additives, see separate calculation tool provided.

Zitrec IC

4 Availability

Zitrec IC is available in bulk and 1000 L containers.

5 Storage requirements & Product handling

The product should be stored above -5°C and preferably at ambient temperatures. Periods of exposure to temperatures above 35°C should be minimized.

The use of pipes galvanized on the interior is not recommended.

Zitrec IC can be stored for minimum 2 years in unopened containers without any effect on the product quality or performance. It is strongly advised not to expose the product in translucent packages to direct sunlight.

It is advisable to store product indoors as the product does not offer freeze protection.

At higher temperatures and in open containers considerable amounts of water can evaporate and this may result in solidification of the product, though without negative effect on the product as the additives are resolvable in water again.

Zitrec IC is a superconcentrate that contains an antifoam agent to limit the foaming during filling operations. Keeping the product in packages for a long time may result in the separation of the antifoam. This can be resolved by stirring or mixing the product prior to its use.

6 Toxicity & safety

For Toxicity and Safety Data we refer to the Material Safety Data Sheet. **Zitrec IC** is not classified under the criteria of Directive 1999/45/EC. The transport is not regulated.

All information contained in this Product Information Leaflet is accurate to the best of our knowledge and belief as at the date of issue specified. However, the Company makes no warranty or representation, express or implied, as to the accuracy or completeness of such information.

Zitrec IC

Addendum - Technical Information

Chemical and physical properties

	Zitrec IC	method
inhibitor content	41 % w/w	
water content	59 % w/w	ASTM D1123
nitrite, amine, phosphate, borate, silicate	Nil	
colour	uncoloured to slightly yellow	
density, 20°C (kg/l)	1.057 typ	ASTM D5931
pH	9.8 typ.	ASTM D1287

ASTM D1384 glassware corrosion tests

	Weight loss in mg/coupon ¹					
	Brass	Copper	Solder	Steel	Cast Iron	Aluminum
ASTM D3306 (max)	10	10	30	10	10	30
6% v/v Zitrec IC in water	1.8	1.1	1.4	0.0	-0.8	6.5

¹ Weight loss AFTER chemical cleaning acc. to ASTM procedure. Weight gain is indicated by a - sign.

ASTM D4340 Aluminum heat rejection test, 25 %

	Weight loss in mg/cm ² /week ¹
ASTM D3306 (max)	1.0
6% v/v Zitrec IC in water	-0.3

¹ Weight loss AFTER chemical cleaning acc. to ASTM procedure. Weight gain is indicated by a - sign.

Corrosion protection



HUCHEM

DISTRIBUTOR COMPANY INFORMATION	
Company name	Huchem B.V.
Address	Kraijenhoffstraat 2 4251 LE Werkendam
Country	The Netherlands
Website	www.huchem.nl
Activities	Distribution of chemicals and cleaning products

Information in this publication is believed to be accurate and is given in good faith,
but it is for the customer to satisfy itself of the suitability for its own particular purpose.
No representation, warranty or guarantee is made as to its accuracy, reliability or completeness.