






DRAWN TO PERFECTION

COMPRESSED CHARCOAL

The freedom of charcoal with the control of a pencil

| | | | | | LF |
|---|--------|---|---|---|----|
|  | Light | ● | ● | V | 8 |
|  | Medium | ● | ● | V | 8 |
|  | Dark | ● | ● | V | 8 |

● Blister of 4 (also contains 1 x Tinted Charcoal White)

● Tin of 6 (contains 1 x Light, 2 x Medium, 2 Dark, Tinted Charcoal White and a free sharpener)

Please note that the contents may be substituted at any time with a product equal or superior to that specified.

Key: LF – Lightfastness, V – Vegan-friendly

Lightfastness rating (LF) = 3,4 – FAIR, MODERATE | 5,6 – GOOD, VERY GOOD | 7,8 – EXCELLENT | V – Vegan-friendly.

Derwent uses the Blue Wool test (ISO 105) to evaluate lightfastness. Lightfastness refers to the chemical stability of a pigment under long exposure to light. A scale of 1-8 is obtained, with values of 6 or higher being considered to be highly lightfast and, under museum conditions, will not fade for 100+ years.