

# PLA



its full term is Poly-Lactic Acid and it is a thermoplastic polymer. Because it is derived from natural sources like corn and sometimes sugarcane, PLA is sometimes referred to a bioplastic. The majority of other thermoplastics are distilled from non-renewable resources like petroleum.

In addition, because it is a natural product, it is also long-term biodegradable. This means that when discarded into a composting system, PLA will naturally break down into its constituent parts typically within a few years.

## Pros

- Can be printed on a cold surface
- more environmental-friendly
- shinier and smoother appearance
- More detail

## Cons

- Can deform because of heat
- Less sturdy

## Uses

- Consumer products

### 1. Identification of the material

Trade name	PLA Poly-Lactic Acid
Chemical name	3D printing
Use	Netherlands
Origin	

### 2. Material properties

Melt temperature	145-160	°C	ASTM D3418
Glass transition temperature	146-60	°C	ASTM D3419
Heat distortion temperature HDTB (0,45 MPa)	56	°C	ISO 75 ASTM
Vicat Softening Temperature	60	°C	D1525 ASTM
Met Flow Rate (210 C/2.16 kg)	9,56	g	D1238 ASTM
Density	1.24	g/cm <sup>3</sup>	D790 ASTM
Water absorption, 24 u	0.1	%	D570 ASTM
Shrink rate	0.5 - 0.7	%	D955

### 3. Mechanical properties

Tensile Strength (break, 3.20 mm/50 mm/min)	52	MPa	ISO 527
Tensile Modulus (3.20 mm/1.0 mm/min)	1320	MPa	ISO 527
Tensile elongation, (break, 3.20 mm/50 mm/min)	5	%	ISO 527
Flexural Modulus (3.20 mm/15 mm/min)	3600	MPa	ISO 178
Flexural Strength (3.20 mm/15 mm/min)	108	MPa	ISO 178
Rockwell hardness (R-scale)	95		ASTM D785

### 4. Printer settings

Printer	Desktop FFF printer
Nozzle	0.4 mm
Layer height	0.2 mm
Infill	100% ±45
Extrusion Temperature	190 - 220 °C
Bed temperature	46 - 60 °C
Bed preparation	Glass, 3DLAC
Print speed	20-40 mm/sec
Requirements	Cooling fan

*Disclaimer: The technical data contained on this data sheet is furnished without charge or obligation and accepted at the recipient's sole risk. This data should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.*