

tesa® 4965 Original

Product Information

Double-coated tape with high shear and temperature resistance

Product Description

tesa® 4965 is a transparent double-sided self-adhesive tape consisting of a PET backing and a modified acrylic adhesive.

tesa® 4965 features:

- Reliable bond even to LSE substrates
- Immediate usability after assembly
- · Suitability for most demanding applications such as heavy stress, high temperatures or critical substrates

Application Fields

- · Mounting of ABS plastic parts in the car industry
- · Self-adhesive mounting of rubber/EPDM profiles
- · Mounting of decorative profiles and mouldings in the furniture industry
- · Mounting of battery packs, lenses and touch-screens in electronic devices

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

•	Backing material	PET film	•	Colour	transparent
•	Type of adhesive	tackified acrylic	•	Total thickness	205 um

Properties/Performance Values

•	Ageing resistance (UV)	very good	•	Static shear resistance at 40°C	very good
•	Chemical resistance	good	•	Tack	good
•	Elongation at break	50 %	•	Temperature resistance long	100 °C
•	Humidity resistance	very good		term duration	
•	Softener resistance	good	•	Temperature resistance short	200 °C
•	Static shear resistance at 23°C	very good		term duration	
			•	Tensile strength	20 N/cm



tesa® 4965 Original

Product Information

Adhesion to Values

 ABS (initial) 	10.3 N/cm	 PET (after 14 days)
 ABS (after 14 days) 	12 N/cm	 PP (initial)
 Aluminium (initial) 	9.2 N/cm	 PP (after 14 days)
 Aluminium (after 14 days) 	10.6 N/cm	 PS (initial)
 PC (initial) 	12.6 N/cm	 PS (after 14 days)
 PC (after 14 days) 	14 N/cm	 PVC (initial)
PE (initial)	5.8 N/cm	 PVC (after 14 days)
 PE (after 14 days) 	6.9 N/cm	 Steel (initial)
PET (initial)	9.2 N/cm	 Steel (after 14 days)

Additional Information

Liner variants:

PV0 red MOPP-film (80μm; 72g/m²) PV1 brown glassine paper (71μm; 82g/m²)

PV4 white with blue tesa® logo PE-coated paper (118µm; 120g/m²)

PV7 transparent PET-film (50μm; 72g/m²) PV11 white PET-film (50μm; 72g/m²)

PV36 double-liner: red MOPP-film (80μm; 72g/m²) and brown glassine paper (71μm; 82g/m²)

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



9.5 N/cm

6.8 N/cm

7.9 N/cm 10.6 N/cm 12 N/cm

8.7 N/cm

13 N/cm 11.5 N/cm

11.8 N/cm