

Product Description Pressure sensitive polymeric vinyl suitable for and flat and contoured surfaces. The film is suitable for wet and dry applications.

Colours 15 gloss

Technical Information

Film Calendered P.V.C.
Thickness film (without adhesive) 75 +/- 3% μm (Op. Istr. n° 4)

Liner Release Clay coated paper 1 side siliconised
70 +/- 20 cN/20 mm

Adhesive Acrylic high tack, difficult to remove
Grammage 45 +/- 10 g/m²
Adhesion after 20 min.: min. 900 N/m. Peel 180° at 20°C on steel (Op. Istr. n° 7)
Adhesion after 72 h. min. 1000 N/m. Peel 180° at 20°C on steel (Op. Istr. n° 7)
Shrinkage < 1 mm after 48 h. at 70°C on steel (Op. Istr. n° 8)

Application temperature Suggested between 10°C and 28°C
Method of application Dry

Temperature resistance from -50°C to +90°C adhered to steel no variation (Op. Istr. n° 15)
Seawater resistance Adhered to steel no variation after 100 h at 20°C (Op. Istr. n° 14)

Reaction to fire classification B-S2-D0 (Standard EN 13501-1:2007+A1
Classification report CSI n° 0626DCREA14_3)