

**General description** A top-coated bright brushed silver coloured metalized polyester film, coated with a permanent acrylic adhesive , backed with a kraft release liner.

Physical properties	VALUE	TEST METHOD
Thickness (micron)	Film: 50 +/- 10 % Adhesive: 25-28 +/- 3 Liner: 79 +/- 10%	ASTMD 3652
Dimensional Stability (%)	Machine Direction No shrinkage observed	On AL panel at 70°C for 24 hr.

Adhesion properties **	Adhesion from (N/25mm) AVERAGE	TEST METHOD
Stainless steel	17	FTM 1 (72 hr dwell time)
Acrylic	20	
Glass	19	
Polypropylene	13	
Expected shear (hours)	100	FTM 8
Tack (gm/sq cm)	540	ASTM D 2979

\*\* For guidance only.

This data is based on limited test results on adhesive coat weight of: 22 micron micron. Due to the custom nature of this product, not to be used for setting specifications.

Technical data	Expected exterior life:	Two years
	Service temperature range:	-40°C to 150°C
	Minimum application temperature:	2°C
	Storage stability:	Two years stored at 21°C and 50% RH

#### Product Performance and Suitability

The above specification is based on information obtained from the original manufacturer and is offered in good faith in accordance with the companies conditions to determine fitness for use. No guarantee is offered or implied. It is the ultimate users responsibility to fully test the material and determine its suitability for the application intended. Measurements and test results are nominal. In accordance with a policy of continuous product improvement the manufacturer reserves the right to amend the specification without notice.