

Customer: **Black Star Bikes** Contact person: Imke Harms EFBE Date of Order: 2013-01-15 Fax-No.:

Landabsatz 25, D-45731 Waltrop tel + 49 (0) 2309 78407-0 fax -10 info@efbe.de www.efbe.de

TestreportMaximum load + Overload test Bicycle frame Test item no. 134188

Test sample data

Manufacturer: **Black Star Bikes**

Model name: Male Identity no.: No Suspension: No Coating: Yes comparison weight (g): 2870 Fork length (mm): 450

Application: Trekking/City

Frame height (cm) 62 Remarks None

Test description

Impact test frame/fork EN 14764 (RGIFMENS)

The frame-fork unit is subjected to an Impact test with falling mass. The test method is corresponding EN 14764, Abs.4.8.2: weight 22,5 kg, drop height 180 mm.

The requirements are corresponding EN 14764, Abs.4.8.2: no crack or fracture or displacement more than 30 mm where a fork is fitted or 10 mm where a solid steel bar is fitted in place of the fork.

Test result:

Permanent deformation: 9.0 mm Crack or fracture: No

The Impact test was passed.

Remarks: For preceded tests please see testreport No. P1306581.

Test engineer: i.A. V. Stobberg

End of testing: 2013-02-15 Waltrop 2013-02-20

stamp, sign

This test report may not be reproduced but with complete wording. It contains the result of a one-time type testing and no statements about quality of serial production components are made. Readings of dimensions, torques and weights without engagement.

Testreport: P1306582 - 1 -



Customer: Contact person: EFBE Date of Order: Fax-No.:

Imke Harms 2013-01-15

Landabsatz 25, D-45731 Waltrop tel + 49 (0) 2309 78407-0 fax -10 info@efbe.de www.efbe.de

Black Star Bikes

TestreportComputer controlled fatigue test of a Bicycle frame Test item no. 134188

Test sample data

Manufacturer: **Black Star Bikes**

Model name: Male Identity no.: No No Suspension: Coating: Yes comparison weight (g): 2870 Fork length (mm): 450

Trekking/City Application:

Frame height (cm) 62 Remarks None

Test description

The frame was fatigue tested following EFBE-Standard 7520. This means a computer controlled and documented single stage test (Wöhler-test) with an error less than 1% and a standard deviation less than 0,5%.

In case of suspension test samples the test is carried out with spring rate, spring preload and damping at maximum.

Fatigue test frame saddle load EN 14764 (RDFSENS)

Test method and requirements are following EN 14 764, clause 4.8.4. for trekking/city bikes:

Test load (pulsating): 1025 N Allocated number of cycles: 50 000

Test result:

The allocated number of loads was reached without any crack or fracture.

The test was passed.

Remarks: None

M. Schröder Test engineer:

End of testing: 2013-02-11 Waltrop 2013-02-20

stamp, sign

This test report may not be reproduced but with complete wording. It contains the result of a one-time type testing and no statements about quality of serial production components are made. Readings of dimensions, torques and weights without engagement.

> Caution! Fatigue tested parts cannot be used further on. Acute danger of fracture!

> > Testreport: P1306581 - 1 -



Customer: Contact person: EFBE Date of Order: Fax-No.: Black Star Bikes Imke Harms 2013-01-15

Landabsatz 25, D-45731 Waltrop tel + 49 (0) 2309 78407-0 fax -10 info@efbe.de www.efbe.de

Testreport

Computer controlled fatigue test of a Bicycle frame Test item no. 134188

Test sample data

Manufacturer: Black Star Bikes

Model name: Male Identity no.: No Suspension: No Coating: Yes comparison weight (g): 2870 Fork length (mm): 450

Application: Trekking/City

Frame height (cm) 62 Remarks None

Test description

The frame was fatigue tested following EFBE-Standard 7520. This means a computer controlled and documented single stage test (Wöhler-test) with an error less than 1% and a standard deviation less than 0.5%.

In case of suspension test samples the test is carried out with spring rate, spring preload and damping at maximum.

Fatigue test frame jump EFBE SP-S (RDGSPS)

The **test arrangement** is simulating jumping, braking and riding over obstacles. Push and pull loads are applied to the dropouts of a dummy fork, direction vertical to the fork stem. Reaction forces are absorbed vertically by the bottom bracket and by the rear axle corresponding to the resulting force.

The requirements are corresponding EFBE-class Standard Performance for trekking/city bikes (SP-S):

Top load (against direction of travel): + 250 N **Bottom load** (into direction of travel): - 500 N **Allocated number of loads:** 100 000

EN 14764 (Trekking/City bike) makes no demands here.

Test result:

The allocated number of loads was reached without any crack or fracture.

The test was passed.

Remarks: For preceded tests please see testreport No. P1306581, P1306582

Test engineer: M. Schröder

End of testing: 2013-03-02 Waltrop 2013-03-06

stamp, sign

This test report may not be reproduced but with complete wording. It contains the result of a one-time type testing and no statements about quality of serial production components are made. Readings of dimensions, torques and weights without engagement.

Caution!
Fatigue tested parts cannot be used further on.
Acute danger of fracture!

Testreport: P1306684 - 1 -