



Quick Tips

SURFACE PRIMER FOR PLASTIC METAL & RESIN FOR MODEL KITS & MINIATURES



MADE IN ITALY



POWERED BY:



by MIG Jimenez



1. Make sure that the surface to be primed is clean and dry

Hay que asegurarse bien de que la superficie a imprimir esté limpia y seca

2. Shake the spray can for at least 30 seconds

Agitar bien el bote al revés al menos durante 30 segundos

3. Spray in several thin layers of color at a distance of 15/20 centimeters whilst rotating the model to avoid accumulation of paint. Allow to dry for at least 15 to 45 minutes depending on the primed surface

Rociar en varias capas delgadas de color a una distancia de 15/20 centímetros rotando la figura para evitar acumulaciones de la pintura. Dejar secar entre 15 a 45 minutos dependiendo de la superficie imprimada

4. The new Titan & AMMO spays can be used as a primer and/or as a base colour for plastic, resin and metal surfaces. They can be painted directly on top of, with acrylics, lacquers and enamels. As can be seen in these SPACE MARINE figures, primed with ROYAL RED MATT PRIMER and SPACE BLUE MATT PRIMER

Los nuevos spays de Titan & AMMO se pueden utilizar como imprimación o como color base para superficies de plástico, resina y metal. Se puede pintar directamente sobre el color con acrílicos, lacas y esmaltes, como se puede apreciar en estas figuras, de la serie SPACE MARINES, imprimadas con el ROYAL RED MATT PRIMER y el SPACE BLUE MATT PRIMER