



12-0068 Ankolux Superhechtprimer

Version 190411	:	waterborne, universal, adhesion primer, for interior use
Composition indication	:	binder : specific acryl/alkyd hybrid technology
Typical characteristics	:	<ul style="list-style-type: none">- good flowout and opacifying power- fast drying- excellent adhesion- to be recoated with waterborne paint systems
Recommended uses	:	interior, as a primary coat resp. an adherent primer for wood, aluminium, stony surfaces, synthetics (hard pvc) and sendzimir galvanized steel. Can be applied over the existing traditional paintwork after first thoroughly cleaning and sanding the surface.
Color(s)	:	white and all colors by the Ankolux tinting system.

Technical specifications (20°C and 65% R.H.)

Solids content	:	approx. 42% (volume)
Density	:	approx. 1,29 gr/cm ³ (white)
Viscosity	:	approx. 8-10 d' Pa's
Gloss	:	semi matt
Drying time	:	<ul style="list-style-type: none">- dustfree : approx. ½ hour- recoatable : approx. 3-4 hours
		* N.B. drying speed/performance is very much dependent of temperature, humidity and particularly air speed circulation!
Application	:	brush, roller
Thinner	:	ready to use (if diluted, max. 5% water)
Cleaning tools	:	water
Application temperature	:	min. 8°C ambient and surface temperature and relative humidity max. 80%.



Theoretical spreading rate	:	at 40 microns dry: approx. 10,5 m ² /ltr
Pretreatment surface	:	<ul style="list-style-type: none"> - painted wood : clean well and rub down - sendzimir zinked steel : if necessary remove dust and zinc salts and degrease - synthetic material : (hard pvc) clean, sand and degrease
	*	the technical data and properties are depending on the color. The stated values are an average.
Storage	:	cool and frost-proof.
Shelf life	:	minimal 12 months in unopened tin.
Special note	:	for more information, see the safety data sheet of this product.

Disclaimer

The information given in this technical data sheet is only a general product description, based on our experiences and tests and therefore does not represent a specific practical case. Consequently Anker Stuy Verven doesn't guarantee the functionality or result and takes no responsibility in this respect. We advise our clients to test the applicability of the product to the nature and the state of the surfaces and to carry out the necessary representative tests in case of doubt. Please contact our R&D department as the occasion arises. Attention: our clients should verify whether the present technical data sheet hasn't been replaced by a more recent version.

