HYDROTOP (Gloss 39/semigloss 40/semi-matt 41)

11-0139/40/41



PRODUCT DESCRIPTION

Water-borne intermediate and finishing coat based on TriCryl ®. Technology for brush application onto exterior or interior timber surfaces especially suited for windows and doors.

TECHNICAL DATA

Viscosity approx. ca. 8 Pa⋅s at 20°C **Density** approx. 1,16 (white) kg/l

Flashpoint Not flammable Method: Closed Cup

Solid content38% by volumeTheoretical spreading rate10-15 m^2 /litreStorage stability12 months at 5° C - 35° C

APPLICATION METHOD Brush, roller, spray (cup) for horizontal

PRODUCT PREPERATION Ready for use - stir well before use

Best results are achieved if finished on a finely sanded surface and applied generously. When applying to previously applied paint coats, we recommend cleaning and degreasing them thoroughly and then sanding them.

RECOMMENDED NO. OF COATS: 2

REQUIRED FILM THICKNESS: 70-100μm **MAXIMUM FILM THICKNESS:** 150μm

SUBSTRATE PREPERATION:

Suitable for all commonly used timber species. Timber moisture content should be between 12 and 16%. The substrate must be clean, dry and free from dust, dirt, grease, silicone and wax. Follow the appropriate Anker Stuy coating specification for other system products such as top coats and end grain sealers.

OTHER INFORMATION:

Cleaning Clean tools and equipment with warm water

Thinning As required

Storage Store in a cool environment and ensure its free from frost.

Shelf Life 1 year if stored correctly
Safety Info Please see Safety Data Sheet

VOC content 121q/l

Version 12072023

MAIN PROPERTIES

Quick drying Ease of use Brushable Low VOC outdoor/indoor

MINIMUM RECOMMENDED SETTINGS

Air Assisted Airless (AAA) Minimum pump size 15:1

Fluid Pressure: n/a
Air Assistance: n/a
Tip Size (Thou.): n/a
Filter size n/a

Airless

Fluid Pressure: n/a
Tip Size (Thou.): n/a

Conventional

Fluid Pressure: Compliant Tip Size (mm): 2.5mm

DRYING TIMES

Drying at: 20°C and relative humidity of 65%

Dust free:60 minutesHandle:60 minutesSanding:90 minutesOvercoat:3 hoursStack:3 hours

This product is suitable for use with Hydrolux system as an on-site touch up product, or maintenance product to recoat existing painted windows and extend lifespan.

* Drying requires good air movement and removal of humid air from confined spaces.