



SUGGESTED PRINT SETS (1)			
Suggested print sets	unit	value	test method
extruder temp	°C	240°-270°	internal
plate temp	°C	50°-80°	internal
min. nozzle diameter (2)	mm.	0.5	internal
fan	%	0-10	internal
print speed	mm/l°	35	internal
PROPERTY			
Physical			
Specific gravity	g/cm ³	1,25	ISO 1183
Water absorption at equilibrium	%	<0,3	23°C / 24 h
Mechanical at 23°C / 50% rh			
Tensile strength	MPa	170	ISO 527
Elongation	%	2	ISO 527
Modulus of elasticity	GPa	15	ISO 527
Charpy impact strength	kJ / m ²	47	ISO 179 1eU
Thermal			
Heat distortion temp.	°C	240°	ISO 75
Continuous service temp.	°C	150	UL746B
Maximum (short term) use temp.	°C	180	-
Coefficient of thermal expansion	10 ⁻⁵ /K	0,4	DIN 52752
Thermal conductivity	W/mK	1	HOT-DISK
Electrical			
Insulation resistance	Ω	≤10 ²	DIN/IEC 60167
Surface resistance	Ω	<10 ²	DIN IEC 60093

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .



ADDITIONAL INFORMATIONS

In general filaments made with PAHP Carbon can be processed on conventional 3D printer using FDM / FFF technology.

PAHP Carbon is a special polyamide carbon fiber reinforced developed for 3D printing and to obtain best results we recommend pre drying the filaments at 120° for 4-6 h. Increase drying time for spools up 1 kg.

Don't leave the filament stopped inside the nozzle more than 20 min. If that down the temperature under 210°, better stop the thermal control.

(1) Suggested print set merely represent a recommendation for general use . Every printer necessity a specific set , nozzle temp, bed temp, etc .

(2) 0.5 mm is the minimum diameter of the nozzle with carbon fibers reinforced. Carbon fibers are abrasive, we suggest to use a nozzle in hardened or tempered metal, like Widia, or wear resistance internal surface, like ceramics or other.
NO tefloned surface!

Disclaimer

The above information is provide in good fact .Treedfilaments is not responsible for any processing which may occur to product finished articles , packaging materials and other .

Further Treedfilaments makes no warranty or representation of any kind regarding the information given or the product described and expressly disclaims all implied warranties , representations and conditions , including without limitation all warranties and conditions of quality , merchantability and suitability or fitness for particular purpose .