

## TECHNICAL DATE SHEET

ABSspeciale

### PROPERTIES

PROPERTIES	VALUE	METOD AND CONDICTION
PHYSICAL & MECHANICAL	Density	1,03 g/cm <sup>3</sup>
	Izod notched impact strength	36 kJ/m <sup>2</sup>
	Ball indentation hardness	74 MPa
	Tensile strength	38 MPa
	Tensile Modulus	1900 MPa
	Flexural strength	56 MPa
THERMAL	Heat Deflection Temperature	85 °C
	Melting point	220 °C
	Flammability:	HB

### SUGGESTED PRINTER SETTING

	VALUE	UNIT
Extruder Temperature	230 - 250	°C
Print Speed	40 - 75	mm/s
Bed Material	70 - 80	°C
Drying Temperature	70 - 80	°C for 2-4 hr

### PRODUCT DETAILS & CERTIFICATION

Diameter	1,75 mm 2,85 mm	Tolerance ± 0,05mm Tolerance ± 0,1mm
----------	--------------------	---

The information supplied in relation to our products recommendations or otherwise, is collected from source considered to be dependable or internally developed. Ciceri de Mondel Srl assumes no liability and makes no warranties of any kind about the accuracy of this datas. The user assumes all responsibility for the use of all information provided and shall.