

TECHNICAL DATE SHEET

ALFAPLUS

BASE MATERIAL: Polylactic acid

PROPERTIES

PROPERTIES	VALUE	ABS	PLA	PET-G	
PHYSICAL & MECHANICAL	Density	1,24 g/cm ³	ISO 1183		
	CHARPY (test 80x10x4 mm)	25 kJ/m ²	ISO 179-1eU		
	Elongation at break:	- Untreated	4,10%	ISO 527	
		- Annealed	2,35%	ISO 527	
	Tensile strength at break:	- Untreated	43 Mpa	ISO 527	
		- Annealed	51 Mpa	ISO 527	
		Flexure Modulus:	- Untreated	3070 Mpa	ISO 527
	- Annealed		4100 Mpa	ISO 527	
THERMAL	Heat Deflection Temperature	- Untreated	58 °C	ISO 75	
		- Annealed	110 °C	ISO 75	

SUGGESTED PRINTER SETTING

	VALUE	UNIT
Extruder Temperature	190 - 210	°C
Print Speed	40 - 120	mm/s
Bed Material	0 - 50	°C
Annealing Temperature	100 °C for 2-4 hr	with any support material (suggested in sand)

PRODUCT DETAILS & CERTIFICATION

Diameter	1,75 mm 2,85 mm	Tolerance ± 0,05mm Tolerance ± 0,10mm
----------	--------------------	--

The information supplied in relation to our products recommendations or otherwise, is collected from source considered to be dependable or internally developed. Ciceri de Mondel Srl assumes no liability and makes no warranties of any kind about the accuracy of this datas. The user assumes all responsibility for the use of all information provided and shall.

Filoalfa by Ciceri de Model Srl
Via Galvani 13, 20080
Ozzero (MI)