Departs-SHOP.COM

SPECS & INFORMATION

U

SEMPERIT (5)

۱_

SM1[®]-STRAHLMEISTER[®]

Shotblast - 12 bar - EN ISO 3861

Application:

_ |

Premium shot blast hose with unique tube quality, for conveying highly abrasive media such as quartz sand, steel shot, corundum, glass, etc.

Feature:

Extremely long service life due to the high abrasion resistant quality of the tube.

Average wear of the tube 36 $\rm mm^3$ (according to DIN ISO 4649:2014).

Antistatic construction prevents the build-up of static electricity.

Standard/approval:

Exceeds EN ISO 3861:2008.

Notice:

A reinforced insert package for increased stability is available upon request.

Temperature range:

-35°C / +80°C.

Safety factor:

3,5 : 1

Tube:

NR/BR/SBR, black, highly abrasion resistant, electrically conductive, smooth.

Reinforcement:

Textile wrapped.

Cover:

SBR, black, resistant to ozone and weather, antistatic, cloth impression.

Marking:

continuous mylartape, yellow letters: "SEMPERIT (S) SM 1[®] - STRAHLMEISTER[®] Sandstrahl / Shotblast WP 12 bar MADE IN EU /////".



Article number	Internal-Ø in		Wall width	External-Ø	Work. pressure	Number of inserts	Bending radius	Weight approx.	Coil length
	mm	inch	in mm	in mm	(max.) bar		(min.) in mm	kg/m	(max.) m
48383 1370	13,0	1/2	7,0	27,0	12	2	130	0,50	40
48383 1950	19,0	3/4	5,0	29,0	12	2	190	0,45	40
48383 1970	19,0	3/4	7,0	33,0	12	2	190	0,65	40
48383 2570	25,0	1	7,0	39,0	12	2	250	0,80	40
48383 3280	32,0	1 1/4	8,0	48,0	12	2	320	1,10	40
48383 3212	32,0	1 1/4	12,0	56,0	12	4	320	1,80	40
48383 3890	38,0	1 1/2	9,0	56,0	12	2	380	1,50	40
48383 3811	38,0	1 1/2	11,1	60,2	12	2	380	1,95	40
48383 4290	42,0		9,0	60,0	12	2	420	1,65	40

Please note: Before using our products with new or untested media, or for applications that are not clearly indicated in the product information, written advice must be obtained from a specialist dealer or a Semperit application engineer. For safety reasons, all products must be inspected regularly for operational safety and replaced in the event of any damage (especially of the cover) or unusual signs of wear and tear. All products must be stored, handled and maintained in accordance with all our respective instructions and DIN 7716:1982. The information in our catalogue as well as each individual datasheet is subject to change at any time without notice since we are constantly developing and improving our products and due to constant technical developments after the latest release date of the catalogue and/or individual datasheets. In order to always have the latest product and safety information make sure you visit our website (www.semperflex.com) regularly or contact one of our specialist dealers or a Semperit application engineer. All contracts with Semperflex are exclusively aut general information about the range, choice and safe use of our products can be found at our website (www.semperflex.com) and must be followed without exception. Important notice: Our catalogue and any individual datasheet have been prepared with great care in order to provide you with all the information you need. The information contained therein is based on the latest state-of-the-art industrial technology and many years of experience and testing: whenever indicated for a certain product, we also confirm conformity with the resistance requirements of the media listed in ISO TR 7620:2005(E). However, the individual conditions of storage, maintenance and use decisively affect the safe and durable use of each product. The quality and safety of our products as indicated in the cast logue or individual datasheets are therefore stirctly subject to the continuous observance of all specifications reparting resistance to chemicals and our cleaning procedures. We reject any liability for safety issues or other consequences due to improper product choice, maintenance or handling (e.g. squashing, rupturing, stretching or filling with non-approved media). Our products must not be used in airplanes or other aerial vehicles under any circumstance. Unless specified otherwise, all hoses are manufactured according to ENISO 1307:2008.



T.



H

5

K,

and a second sec

V.

-

AND DE LE COLORIZACIÓN DE LE COL

ANN A

AMM -

info@iq-parts.nl Harsweg 34A 2461 EZ Ter Aar T +31 252 624 126 The Netherlands