

EASY PATTERNS

SPECIFICATIONS

*	+	Carrier	♀		
Composition	Avarage Thickness		Certifications		
PU	90 microns	Adhesive polyester	REACH n° 1907/2006/EU OEKO-TEX ® COMFIDENCE IN TEXTILES STANDARD 100		

APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS $~~\downarrow~~$			TRANSFER SETTINGS			\checkmark
		≟	>>	0			•
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	50 gf	25 cm/sec	15"seconds	155°C (311°F)	Medium (2,5/3,5 bar)	hot

- \rightarrow Print, cut, and weed material
- → Remove the print from the carrier by hand and place it on the garment
- → Cover the print with silicon or parchment paper
- → Heat apply at the conditions shown above
- → *TTD Special application tape is required when designs have multiple pieces that need to be kept in alignment. Peel it hot

PRODUCT HIGHLIGHTS

- \rightarrow perfect for kidswear
- \rightarrow quick application time + low temperature
- → deep, rich colors

NOTE: Given the large number of sublimation inks and printers, we highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

₩ Washing	Reference to the second	⊙ Tumble dry	O Dry cleaning	C Storage Shelf Life	े Storage Temperature	C Storage Conditions	⊲ ⊳ Position
Up to 40°C, best inside-out	YES best inside-out	NO	NO	Up to 2 year	Between 18°C and 26°C	Away from sunlight and dust	Vertical

 \rightarrow Wait 24 hours after the application before the first wash

- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our Sales Office.



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246

