

















STRIPFLOCK PRO

SPECIFICATIONS

	 Composition	 Average Thickness	 Carrier	 Oeko-Tex	 Certifications
Stripflock Pro standard colors*	PVC	650 microns	Adhesive Polyester	class I	REACH n° 1907/2006/EU OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100  VEGANOK  ADEGAN N. 1004 
Stripflock Pro fluo colors	PU	620 microns		class II	

*Stripflock Pro black Oeko-Tex standard 100 class II

APPLICATION INSTRUCTIONS

 Applies on	SUGGESTED CUTTING SETTINGS ↓			TRANSFER SETTINGS ↓			
	 Blade	 Pressure	 Speed	 Time	 Temperature	 Pressure	 Peel
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	60°	60 gf	15 cm/sec	15 seconds	155°C (311°F)	Medium (2,5/3,5)	warm









- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier warm

PRODUCT HIGHLIGHTS

- velvet touch
- embroidery look

 **NOTE:** Stripflock Pro cannot be layered on itself. We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

 Washing	 Ironing	 Tumble dry	 Dry cleaning	 Storage Shelf Life	 Storage Temperature	 Storage Conditions	 Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 year	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

 This document can be subject to variations. Updated versions are available on www.siser.com For further information, please contact our Sales Office.



Siser s.r.l.
Viale della Tecnica, 18
36100 Vicenza - Italy

Tel. +39 0444.287960
Fax +39 0444.287959
info@siser.it
www.siser.com

r.e.a. vi 171856
reg. imp. vi n° 14971
c.s. € 103.300 i.v.
p.iva 01591490246



Management System
ISO 9001:2015
ISO 14001:2015

